

Dr. P. H. Leake

Original: Mr. Runyon
cc: Files
PRC
TPP

AT-PM-354

NYO 1266 (8-71)

MATERIAL TEST REQUEST

REQUEST (SECTION A) This Section Completed By Originator

ORIGINATOR Robert E. Logler	DEPARTMENT Purchasing	DATE 12/28/73
LOCATION New York Office	VENDOR CODE OR OTHER REFERENCE Peter J. Schweitzer Division	PROCUREMENT PROJECT NUMBER

REASON FOR TEST REQUEST

SAVINGS SUBSTITUTE MATERIAL IMPROVE QUALITY ADDITIONAL SOURCE SPEC. CHANGE (SIZE, ETC.) OTHER (EXPLAIN)

DESCRIPTION OF MATERIAL AND PROPOSED APPLICATION (INCLUDE ANY SPECIAL INSTRUCTIONS OR PREFERRED TEST CONDITIONS AND SUPPLIER TEST RESULTS IF AVAILABLE)

Samples of Peter J. Schweitzer Cork Base Tipping Paper - 32-33 grams/sq. meter are attached. Supplier claims these grades will perform at superior rate on makers to present stock ordered by Golden Belt. Efficiency is obtained from better dimensional stability and similar machine settings which is the result of using one uniform weight of paper for differing filter lengths.

Please make usual evaluation test and comparison test with cork base paper supplied by Ecusta Paper Operations.

If you require samples of cork base paper made by Ecusta to accomplish the requested test, please contact Mr. Logler of the Purchasing Department.

PRELIMINARY APPROVALS TO TEST	MANUFACTURE <i>P. Runyon</i>	DATE 1/3/74	RESEARCH AND DEVELOPMENT <i>A. H. Giffis</i>	DATE 1-8-74
	QUALITY CONTROL <i>P. Hecke</i>	DATE 9 Jan 74	OTHER	DATE
TESTING TO BE DONE AT			QUANTITY REQUIRED	
SPECIAL INSTRUCTIONS				

RESULTS (SECTION B) This Section Completed By Tester

<input type="checkbox"/> MATERIAL APPROVED	<input type="checkbox"/> NOT APPROVED (EXPLAIN WHY)		
COMMENTS	R. & D. No. G7-74 P.J. Schweitzer Ecusta TOD 2313		
Odor	Acceptable	Acceptable	
Thickness, ins.	0.0020	0.0019	
Wt, gm/M ²	33.4	31.4	
Tensile, gm	6,540	5,580	
Stretch, %	1.5	1.5	
Ash, %	17.6	15.7	
Porosity, sec/50 cc	608	241	
Absorption, gm/M ² - Front	40.8	42.0	(See reverse side)
Back	44.3	43.2	

FINAL APPROVALS	TESTER	DATE	MANUFACTURE	DATE
	LOCAL QUALITY CONTROL	DATE	OTHER	DATE
	QUALITY CONTROL	DATE	REC'D IN PROCUREMENT	DATE

NOTE: HANDLE CAREFULLY. COMPLETE YOUR PORTION LEGIBLY. THIS CARD WILL BE INCLUDED IN PROCUREMENT PERPETUAL FILE. WHERE REQUIRED, MAKE XEROX FOR LOCAL FILES;

Since laboratory evaluation of the Schweitzer cork-base tipping paper indicates this material to be satisfactory, we recommend that a sufficient quantity be printed to produce at least six bobbins of tipping for evaluation at one of the branches.

J. H. Ke
9 Jan '74

